

RELIABILITY REPORT



**RELIABILITY DATA
LT1575 / LT1577**

8/21/2006

• OPERATING LIFE TEST

PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE CODE	NEWEST DATE CODE	K DEVICE HOURS ⁽¹⁾ AT +125°C	NUMBER OF ⁽²⁾ FAILURES
SOIC/SOT/MSOP	228 228	9640	9640	126.83 126.83	0 0

• PRESSURE COOKER TEST AT 15 PSIG, +121°C

PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE CODE	NEWEST DATE CODE	K DEVICE HOURS	NUMBER OF FAILURES
SOIC/SOT/MSOP	802 802	9640	0413	19.35 19.35	0 0

• TEMP CYCLE FROM -65°C to +150°C

PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE CODE	NEWEST DATE CODE	K DEVICE CYCLES	NUMBER OF FAILURES
PLASTIC DIP	100	9720	9730	10.00	0
SOIC/SOT/MSOP	349 449	9640	0006	34.90 44.90	0 0

• THERMAL SHOCK FROM -65°C to +150°C

PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE CODE	NEWEST DATE CODE	K DEVICE CYCLES	NUMBER OF FAILURES
SOIC/SOT/MSOP	224 224	9640	0207	22.40 22.40	0 0

(1) Assumes Activation Energy = 1.0 Electron Volts

(2) Failure Rate Equivalent to +55°C, 60% Confidence Level = 14.50 FITS

(3) Mean Time Between Failures in Years = 7,867

Note: 1 FIT = 1 Failure in One Billion Hours.