

# RELIABILITY REPORT



## RELIABILITY DATA

### LTC1258

### 8/21/2006

#### • OPERATING LIFE TEST

PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE CODE	NEWEST DATE CODE	K DEVICE HOURS <sup>(1)</sup> AT +125°C	NUMBER OF <sup>(2)</sup> FAILURES
SOIC/SOT/MSOP	176 176	9813	9901	130.08 130.08	0 0

#### • PRESSURE COOKER TEST AT 15 PSIG, +121°C

PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE CODE	NEWEST DATE CODE	K DEVICE HOURS	NUMBER OF FAILURES
SOIC/SOT/MSOP	996 996	9816	0142	69.11 69.11	0 0

#### • TEMP CYCLE FROM -65°C to +150°C

PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE CODE	NEWEST DATE CODE	K DEVICE CYCLES	NUMBER OF FAILURES
SOIC/SOT/MSOP	897 897	9816	0238	133.85 133.85	0 0

#### • THERMAL SHOCK FROM -65°C to +150°C

PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE CODE	NEWEST DATE CODE	K DEVICE CYCLES	NUMBER OF FAILURES
SOIC/SOT/MSOP	248 248	9818	0142	68.90 68.90	0 0

(1) Assumes Activation Energy = 0.7 Electron Volts

(2) Failure Rate Equivalent to +55°C, 60% Confidence Level = 90.99 FITS

(3) Mean Time Between Failures in Years = 1,254

Note: 1 FIT = 1 Failure in One Billion Hours.